

Physical Properties of Molded and Modified EPS

I. ASTM SPECIFICATIONS

Parts molded from Huntsman modified expandable polystyrene (EPS) will comply with the following standards when produced in accordance with the manufacturer's recommendations. Huntsman participated in the development of ASTM-C578 through membership in ASTM, C-578 Committee and Industry Trade Association involvement, and laboratory proficiency testing, including third party verification.

ASTM C-578

"Standard Specifications for Preformed, Cellular Polystyrene Thermal Insulation"

Table 1.0

Classification	Type XI	Type I	Type VIII	Type II	Type IX	Type XIV
Compressive resistance at yield or 10% deformation, whichever occurs first (with skins intact), min, psi (kPa) per ASTM D1621	5.0 (35)	10.0 (69)	13.0 (90)	15.0 (104)	25.0 (173)	40.0 (276)
Thermal resistance of 1.00-in. (25.40mm) thickness, min, F-ft ² -h/Btu (K-m ² /W) Mean temperature: 75 ± 2°F (24 ± 1°C) per ASTM C-177/C-518	3.10 (0.55)	3.60 (0.63)	3.80 (0.67)	4.00 (0.70)	4.20 (0.74)	4.20 (0.74)
Flexural strength, min, psi (kPa) per ASTM C-203	10.0 (70)	25.0 (173)	30.0 (208)	35.0 (240)	50.0 (345)	60.0 (414)
Water vapor permeance of 1.00-in. (25.40mm) thickness, max, perm (ng/Pa-s-m ²) per ASTM E-96	5.0 (287)	5.0 (287)	3.5 (201)	3.5 (201)	2.0 (115)	2.5 (143)
Water absorption by total immersion, max, volume % per ASTM C-272	4.0	4.0	3.0	3.0	2.0	2.0
Dimensional stability (change in dimensions), max, %	2.0	2.0	2.0	2.0	2.0	2.0
Oxygen index, min, volume % per ASTM D-2863	24.0	24.0	24.0	24.0	24.0	24.0
Density, min, lb/ft ³ (kg/m ³) per ASTM C-303	0.70 (12)	0.90 (15)	1.15 (18)	1.35 (22)	1.80 (29)	2.40 (38)

Thermal Resistance Values at Additional Mean Temperatures

Table 1.1

Property	Type XI	Type I	Type VIII	Type II	Type IX	Type XIV
Density, min, lb/ft ³ (kg/m ³) per ASTM C-177/C-518	0.70 (12)	0.90 (15)	1.15 (18)	1.35 (22)	1.80 (29)	2.40 (38)
Thermal resistance of 1.00-in. (25.4-mm) thickness, min, F-ft ² -h/Btu (K-m ² /W)						
Mean temperature:						
25°F (-3.9°C) +2°F (+1°C)	3.45 (0.61)	4.20 (0.74)	4.40 (0.77)	4.60 (0.81)	4.80 (0.84)	4.80 (0.84)
40°F (4.4°C) +2°F (+1°C)	3.30 (0.58)	4.00 (0.70)	4.20 (0.74)	4.40 (0.77)	4.60 (0.81)	4.60 (0.81)
110°F (43.3°C) +2°F (+1°C)	2.90 (0.51)	3.25 (0.57)	3.45 (0.61)	3.65 (0.64)	3.85 (0.69)	3.85 (0.69)
Classification or Type	XI	I	VIII	II	IX	XIV

II. OTHER PROPERTIES

There are a number of other important characteristics not required by the standards that are frequently requested by specifiers and regulatory agencies. These properties are shown in the following table:

**Huntsman Modified Expanded Polystyrene
Typical Physical Properties at 1 - lb/cu. ft.**

PROPERTY	UNITS	ASTM TEST	VALUE
SHEAR PROPERTIES		C-273	
Ultimate Load	lbs.		370
Shear Strength	psi		16
Shear Modulus	psi		440
TENSION PROPERTIES		C-297	
Ultimate Load	lbs.		490
Tensile Strength	psi		28
Type of Failure			Sudden
Location of Failure			Core
BREAKING LOAD AND FLEXURAL PROPERTIES		C-203	
Breaking Load	lbs.		26
Modulus of Elasticity	psi		915

The information contained herein is provided for general purposes only. By providing the information contained herein, Huntsman, L.L.C. makes no guarantee or warranty, and does not assume any liability with respect to the accuracy or completeness of such information, or the product results in any specific instance and hereby expressly disclaims any implied warranties of merchantability or fitness for a particular purpose, or any other warranties or representations whatsoever, expressed or implied. Nothing contained herein shall be construed as a license to use the products of Huntsman, L.L.C. in any manner that would infringe any patent.